

Fig. 1

Staple fiber to which ester from PEG and fatty acid is applied is provided as raw material, and the staple fiber is opened and carded to obtain a web.

— 10

Binding to obtain non-woven fabric — 11

5

Heat treatment — 12

Electric charging — 13

10 Electret non-woven fabric — 14

FIG. 1